

Metallurgical Coke

Uses: As a fuel and reducing agent in smelting iron ore in a blast furnace.

Proximate analysis:

Ash (%): 13% max.

Volatile matter (%): 2% max.

Fixed carbon (%): 85% min.

Moisture (%): 5% max.

Sulphur (%): 1% max.

Heating power (btu/lb): 11.200 approximate.

Heating power (J/g): 26.000 approximate.

MICUM 40: 80% min.

MICUM 10: 10% max.

